

Technical Data Sheet

Texplan 650g FR

| TECHNICAL SPECIFICATIONS | STANDARDS | UNIT | VALUE |
|---------------------------------|--|--|---|
| BASE FABRIC: | DIN 60 001 | | 100% PES |
| YARN TYPE: | DIN EN ISO 2060 | POLYESTER | 1100 DTX |
| WEAVING CONSTRUCTION: | | | 8X8 (20X20) |
| WEIGHT: | TS 1534 EN ISO 2286-2 DIN EN ISO 2286-2 | gr/m ² gr/m ² | 650 ± 5 |
| WIDTH: | | cm cm | 150-250-300-320 (DEPENDS ON CLIENTS REQUEST) |
| ROLL LENGTH: | | m m | 50-250 (DEPENDS ON CLIENTS REQUEST) |
| SURFACE TREATMENT: | | | GLOSSY-MA TT-EMBOSS |
| TEMPRATURE RESISTANT: | DIN EN 1876-1 | °C | -30 |
| TEMPRATURE RESISTANT: | IVK/Pkt.5 | °C | +70 |
| TENSILE STRENGTH (warp/weft): | TS 2008 EN ISO 1421 EN ISO 1421 | N/5cm | 2500 / 2300 |
| TEAR STRENGTH (warp/weft): | TS EN ISO 4674-1 EN ISO 4674-1 | N | 220 / 200 |
| ADHESION: | TS EN ISO 2411 EN ISO 2411 | N/5cm | 80 |
| COLOUR FASTNESS: | BS EN ISO 105-B02 | | 6+ |
| EXTRA TREATMENT: | ACRYLIC, SIL VER, PVDF LAC | | (IF DEMANDED) |
| FLAMMABILITY (FR): | DIN 4102-1B2 / NF P 92-507 | | B2 / M2 / B1 |

ATTENTION! The above Technical Data has an aritmetical avarage deviation ratio as +/- 5%.