

Subliart Mesh 115g**Fisa tehnica**

Article-No	6953BC
	PES-MESH with INKTeX+BC® treatment for inkjet-direct print with disperse-inks
Material	100% Polyester
Stock widths	app. 253 cm, 310 cm
Finishing	rolled on paper cores
Packaging	wrapped with foil
Ecology	according to Öko-Tex Standard 100, product class IV

Weight acc. to DIN EN 12127	115.00 g/m ²	±3 %
--------------------------------	-------------------------	------

Shrinkage

Heat Shrinkage, 195°C, 90 sec, lengthwise acc. to AA 25-02	-2.00 %	±1 %
---	---------	------

Heat Shrinkage, 195°C, 90 sec, crosswise acc. to AA 25-02	-2.00 %	±1 %
--	---------	------

Tearing strength

Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	40.00 %	±20 %
--	---------	-------

Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	50.00 %	±20 %
---	---------	-------

Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 250.00 N/5cm
--	-------------------

Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 270.00 N/5cm
---	-------------------