

SBO-16

Property	Test Method	Value	Unit
Tensile Strength (WARP/WEFT)	ISO 13934-1 : 2013 C.R.E, STRIP METHOD	1900 1600	N/50mm
Tearing Strength (WARP/WEFT)	ISO 13937-2 : 2000 C.R.E, SINGLE TEAR METHOD	65 65	N
Elongation (WARP/WEFT)	ISO 13934-1 : 2013 C.R.E, STRIP METHOD	23.2 29.0	%
Adhesion Strength (WARP/WEFT)	ISO 2411:1991 C.R.E	70.7 83.8	N/5cm

For more information, visit our website at
www.star-flex.com