

SP-15 TDS

Property	Test Method	Value	Unit
Transmittance	ASTM E 424 1971 6. 5. 2	19	%
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	2065.3 1773.0	N/5cm
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	205.9 166.7	N
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	23.4 28.4	%
Adhesion Strength (warp/weft)	ISO 2411:1991 C.R.E	78.5	N/5cm
Flexing Endurance	DIN 53351, FLEXOMETER METHOD	16000	CYCLES
Resistance to Low Temp. (warp/weft)	ISO 13934-1:1999 -20°C, 5HRS		%
Resistance to High Temp. (warp/weft)	ISO 13934-1:1999 80°C, 5HRS		%
Colorfastness to Weathering	ASTM G 26, METHOD A, TYPE B	3	grade

For more information, visit our website at
www.star-flex.com