

# SIOEN B6303

## Mechanical properties

Breaking strength Warp	4000 N/5cm	ISO 1421/1 : 2016
Breaking strength Weft	3500 N/5cm	ISO 1421/1 : 2016
Tear strength Warp	600 N	DIN 53363 : 2003
Tear strength Weft	500 N	DIN 53363 : 2003
Adhesion	125 N/5cm	ISO 2411 : 2017

## Physical pro

Mechanical properties	Breaking strength Warp	4000 N/5cm	ISO 1421/1 : 2016	NF G 37 106 1986
	Breaking strength Weft	3500 N/5cm	ISO 1421/1 : 2016	
	Tear strength Warp	600 N	DIN 53363 : 2003	
	Tear strength Weft	500 N	DIN 53363 : 2003	
	Adhesion	125 N/5cm	ISO 2411 : 2017	
Physical properties	Temperature resistance	-30/+70 °C	EN 1870/1 : 1998	ISO 105 B02 : 2014
	Light fastness (Except white and (half-)transparent)	7-8	ISO 105 B02 : 2014	ISO 3795 : 1989
	Fire behaviour	< 100 min/min	ISO 3795 : 1989	

## 1 COLOUR

OTHER COLOURS AND WIDTHS ON REQUEST

