













# SIOEN C7456

<b>Mechanical properties</b>	Breaking strength Warp	2500 N/5cm	ISO 1421/1 : 2016
	Breaking strength Weft	1800 N/5cm	ISO 1421/1 : 2016
	Tear strength Warp	250 N	DIN 53363 : 2003
	Tear strength Weft	250 N	DIN 53363 : 2003
	Adhesion	70 N/5cm	ISO 2411 : 2017

<b>Physical properties</b>	Temperature resistance	-40/+70 °C	EN 1876/1 : 1998
	Light fastness (Except white and (half-)transparent)	7-8	ISO 105 B02 : 2014
	Fire behaviour	< 100 mm/min	ISO 3795 : 1989

## 12 COLOURS

OTHER COLOURS AND WIDTHS ON REQUEST

 <p><b>1617</b> - Beige Standard 150 cm × 65 lm</p>	 <p><b>4001</b> - Bordeaux Standard 150 cm × 65 lm</p>	 <p><b>5041</b> - Blue Standard 150 cm × 65 lm</p>	 <p><b>6195</b> - Green Standard 150 cm × 65 lm</p>	 <p><b>7005</b> - Grey Standard 150 cm × 65 lm</p>
 <p><b>7006</b> - Grey Standard 150 cm × 65 lm</p>	 <p><b>7007</b> - Grey Standard 150 cm × 65 lm</p>	 <p><b>7009</b> - Grey Standard 150 cm × 65 lm</p>	 <p><b>7211 (RAL 7047)</b> - Grey Standard 150 cm × 65 lm</p>	 <p><b>7222</b> - Grey Standard 150 cm × 65 lm</p>
 <p><b>7999</b> - Black Standard 150 cm × 65 lm</p>	 <p><b>9002</b> - White Standard 150 cm × 65 lm</p>			