

SIOEN D5361

Mechanical properties

Breaking strength Warp	2100 N/5cm	ISO 1421/1 : 2016
Breaking strength Weft	1500 N/5cm	ISO 1421/1 : 2016
Tear strength Warp	100 N	DIN 53363 : 2003
Tear strength Weft	100 N	DIN 53363 : 2003
Adhesion	60 N/5cm	ISO 2411 : 2017

Physical properties

Temperature resistance	-40/+70 °C	EN 1876/1 : 1998
Light fastness (Except white and (half-)transparent)	7-8	ISO 105 B02 : 2014
Fire behaviour	< 100 mm/min	ISO 3795 : 1989

1 COLOUR

OTHER COLOURS AND WIDTHS ON REQUEST

