

SIOEN G2700

Mechanical properties

Breaking strength Warp	2500 N/5cm	ISO 1421/1 : 2016
Breaking strength Weft	2000 N/5cm	ISO 1421/1 : 2016
Tear strength Warp	270 N	DIN 53363 : 2003
Tear strength Weft	270 N	DIN 53363 : 2003
Adhesion	90 N/5cm	ISO 2411 : 2017

Physical properties

Light fastness (Except white and (half-)transparent)	7-8	ISO 105 B02 : 2014
Temperature resistance	-40/+70 °C	EN 1876/1 : 1998
Fire behaviour	M2	NF P 92-507:2004
Reaction to fire	B(fl)-s1	EN 13501-1 + A1 : 2009

2 COLOURS

OTHER COLOURS AND WIDTHS ON REQUEST

