















Substrate		DIN 60001	100 % polyester (Trevira CS)
Weave		DIN ISO 9354	woven fabric
Weight approx.		DIN EN ISO 2286-2	155 g/m ²
Fire retardancy		DIN 4102 B1, C1, M1, NFPA 701, B-s1,d0*	yes
Sound absorption		EN ISO 11654 ASTM C423	$\alpha_w = 0,45$ NRC = 0,45
Application			indoor
Width		DIN EN ISO 2286-1	240 cm / 94 inch
Print side			one-sided
Roll length			40 m
Type of ink		 	UV-curable inks**, latex inks

Advantages

- matt surface
- no curling
- fast crease recovery
- sound absorbing
- trimming cold (no fraying)

Applications

- frame tensioning systems
- roller, vertical, panel blind

* see General Building Inspectorate Approval of Trevira GmbH

** please consider the risk of curling because UV-curable inks will still be hardening after a while



All details are nominal values and are subject to change within usual tolerances ($\pm 5\%$). The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor. date: 01/2020